AMENDMENTS TO THE CLAIMS

1. **(Currently amended)** A material for dielectric films, which is a polymerizable composition comprising:

an adamantanepolycarboxylic acid represented by following Formula ~~(1)~~: (1a):



~~(1)~~



(1 a)

wherein ~~X~~ X^a is a hydrogen atom ~~atom, a carboxyl group~~ or a hydrocarbon group; and Y^1, Y^2, Y^3 and Y^4 may be the same as or different from one another and are each a single bond or a bivalent aromatic cyclic group;

an aromatic polyamine represented by following Formula (2):



(2)

wherein Ring Z is a monocyclic or polycyclic aromatic ring; and R^1 and R^2 are each a substituent bound to Ring Z, may be the same as or different from each other and are each an amino group, a mono-substituted amino group, a hydroxyl group or a mercapto group; and

a solvent other than ketones and aldehydes,

wherein the adamantanepolycarboxylic acid and the aromatic polyamine are dissolved in the solvent.

2. **(Currently amended)** A polymer which is a polymerized product of a polymerizable composition comprising:

an adamantanepolycarboxylic acid represented by following Formula ~~(1)~~: (1a):



~~(1)~~



(1 a)

wherein ~~X~~ X^a is a hydrogen atom ~~atom, a carboxyl group~~ or a hydrocarbon group; and Y^1, Y^2, Y^3 and Y^4 may be the same as or different from one another and are each a single bond or a bivalent aromatic cyclic group;

an aromatic polyamine represented by following Formula (2):



(2)

wherein Ring Z is a monocyclic or polycyclic aromatic ring; and R^1 and R^2 are each a substituent bound to Ring Z, may be the same as or different from each other and are each an amino group, a mono-substituted amino group, a hydroxyl group or a mercapto group; and

a solvent other than ketones and aldehydes,

wherein the adamantanepolycarboxylic acid and the aromatic polyamine are dissolved in the solvent.

3. **(Canceled)**

4. **(Currently amended)** A dielectric film comprising the polymer of claim 2 ~~or 3~~.

5. **(Currently amended)** A dielectric film comprising a polymer formed from:

an adamantanepolycarboxylic acid represented by following Formula ~~(1)~~: (1a):



(1)



(1 a)

---

wherein ~~X~~ X^a is a hydrogen atom ~~atom, a carboxyl group~~ or a hydrocarbon group; Y^1, Y^2, Y^3 and Y^4 may be the same as or different from one another and are each a single bond or a bivalent aromatic cyclic group; and

an aromatic polyamine represented by following Formula (2):



(2)

wherein Ring Z is a monocyclic or polycyclic aromatic ring; and R^1 and R^2 are each a substituent bound to Ring Z, may be the same as or different from each other and are each an amino group, a mono-substituted amino group, a hydroxyl group or a mercapto group,

wherein the dielectric film has a 5% weight loss temperature of 500°C or higher.